



## **POOL DECK REPAIR KIT**

### A Do It Yourself Pool Patch Repair Kit

Coverage: Approx. 13 Square Feet  
NET WT. 10 lb. (4.54 kg.)

#### **POOL PATCH INSTRUCTIONS**

1. Remove loose pool deck material with putty knife or scraper.
2. Clean repair area with scrub brush using a mixture of 1 part muriatic acid to 3 parts water. Allow mixture to expose area 1 minute and rinse off using a water hose.
3. Use damp sponge to remove excess water from repair area.
4. Add 2 oz. of LIQUID CEMENT BONDER per 1 1/2 lb. of DRY POOL PATCH DECK MIX. Add water and mix until a putty consistency is achieved.
- 5a. FOR CRACK REPAIRS apply WET POOL PATCH DECK MIX into crack with putty knife and wipe excess material with damp sponge. Keep sponge clean by rinsing out often. Allow repair area to dry.
- 5b. FOR SMALL REPAIRS Apply WET POOL PATCH DECK MIX with a trowel at 1/4" thickness onto the repair area. Use toothbrush or fingers to tap entire repair area creating small points or raised areas. Remove excess material from edges with sponge.
- 5c. FOR LARGE REPAIRS apply WET POOL PATCH DECK MIX with a pool deck dash brush to the repair area creating small points or raised areas. Remove excess material from edges with sponge.
6. Once material becomes partially stiff use trowel to knock down texture flat creating a similar texture to existing pool deck. If material becomes too hard to trowel mist repair area with water.

#### **WARNING:**

Contains Cement, an Alkaline substance irritating to eyes and skin. Contains Acrylic Resin Cement Bonder. Should product contact eyes, flush them immediately and repeatedly with water and call a Physician. **DO NOT TAKE INTERNALLY.** In case of skin contact, rinse immediately with water. **USE OF RUBBER GLOVES AND EYE PROTECTION IS RECOMMENDED.**

#### **KEEP OUT OF REACH OF CHILDREN**

Pool Patch, Phoenix, Arizona  
poolpatch.com

Repair Kit Contains Appx. 9 lb. (4.8 kg.) Dry Pool Patch Deck Mix & 12 fl. oz of the Cement Bonder